

# Bruck Norcote Super

**End use:** Magazines, catalogues, supplements, direct mail, inserts/flyers

**Product Family:** Norcote

**Printing method:** Heat set web offset

**Finish:** Gloss

**Producer:** Bruck

Basic properties	ISO										
Basis Weight	(ISO 536)	(g/m <sup>2</sup> )	54*	57	60	65	70	75	80	90	
Thickness	(ISO 534)	(µm)	47	49	50	54	58	62	65	73	
Bulk	(ISO 534)	(cm <sup>3</sup> /g)	0.87	0.86	0.83	0.83	0.83	0.83	0.81	0.81	
Brightness D65	(ISO 2470)	(%)	85	85	85	87	87	87	87	87	
CIE Whiteness	(ISO 11475)	(%)	100	100	100	105	105	105	105	105	
L-value D65	(ISO 5631-2)	(D65/10°)	91	91	92	92	92	92	92	92	
a-value D65	(ISO 5631-2)	(D65/10°)	0.2	0.2	0.2	0.7	0.7	0.7	0.7	0.7	
b-value D65	(ISO 5631-2)	(D65/10°)	-4.5	-4.5	-4.5	-5.3	-5.3	-5.3	-5.3	-5.3	
Opacity	(ISO 2471)	(%)	90	91	92	92	93	94	95	96	
Gloss (Lehmann)	(ISO 8254-1) (Tappi T480)	(%)	48	50	54	56	58	58	58	58	
Smoothness PPS 10	(ISO 8791-4)	(µm)	1.3	1.3	1.2	1.2	1.2	1.2	1.2	1.2	

Last Updated: 16/01/2023